

FILAMENT WINDING



MetPreg™ Filament Winding – A Breakthrough Technology

Metal matrix composite materials are enabling for applications requiring stiffness and strength especially at high temperatures. Filament winding has been around for decades and remains one of the most cost-effective methods for mass production of composites. The confluence of these two technologies, namely a low-cost filament winding process with high-performance metal matrix composite materials, can lead to great improvements in the ability to produce affordable MMC structures by driving down costs and improving manufacturing capabilities.

Touchstone Research Laboratory has developed a process to filament wind its MetPreg metallic prepregs. This breakthrough process can be used for manufacturing cylinders, spheres, or other shapes. Hydrostatic burst testing on finished cylinders has demonstrated translation efficiencies of more than 85%.

This technology is ideal for:


- Rocket motor cases
- Pressure vessels
- Aerospace storage tanks
- Ordnance items
- Hydrogen fuel tanks
- Tubular structures

MetPreg filament wound vessels have excellent burst pressure, longitudinal and torsional stiffness, and compressive strength. The compression strength for these materials can be as high as 4.0 GPa (580 ksi), which makes them ideal for gun-launched ordnance applications where high compressive loads are experienced. These properties are maintained at high temperatures. The benefits offered by this technology could easily provide weight reduction opportunities for structural engineers and designers.



MetPreg™ Filament Winding Features

- Highly repetitive part-to-part fiber placement
- Large structures can be built without costly casting mold investments
- Low-cost manufacturing process
- High fiber volume attainable
- Continuous fiber used over entire component area
- Maintains 85% of its room temperature longitudinal tensile strength to greater than 700°F
- Field repairs are possible with soldering and brazing equipment
- Permeability of H₂ through the aluminum matrix is negligible
- Compatible with liquid O₂ and many propellant chemistries
- Does not microcrack at cryogenic temperatures
- Does not outgas under vacuum
- Properties are unaffected by high humidity
- UV exposure causes no degradation of properties
- Electrically conductive – no static charging
- Coefficient of thermal expansion is approximately half that of aluminum
- Integral flanges and end closures for pressure vessels can be wound-in
- Remains impermeable to He after 100 cycles between -450°F and 250°F



Typical Properties of MetPreg™ Cylinders (50% Fiber Volume Fraction, 4060 psi Burst)

Density (g/cm ³)	3.30
Wall Thickness, in	0.095
Weight per Linear Inch, lb/in	0.24
Internal Volume per Linear Inch, in ³ /in	36.4



The test data presented in this bulletin is believed by Touchstone to be representative of this product. However, the test data are not a guarantee or warranty. Touchstone makes no warranty, whether expressed or implied, including warranties of merchantability or of fitness for a particular purpose. Under no circumstances shall Touchstone be liable for incidental, consequential, or other damages arising out of a claim from alleged negligence, breach of warranty, strict liability or any other theory, through the use or handling of this product or the inability to use the product. The sole liability of Touchstone for any claims arising out of the manufacture, use, or sale of its products shall be for the replacement of the quantity of this product which has proven to not substantially comply with the data presented in this bulletin. Users should make their own assessment of the suitability of any product for the purposes required. The above supercedes any provision in your company's forms, letters, or other documents.